

PRODUCT DESCRIPTION A one pack, aluminium pigmented silicone resin coating.

INTENDED USES As a light reflective primer/finish for surfaces that can reach dull red heat of up to 540°C (1004°F), such as exhaust stacks
 For use at Newbuilding, Maintenance & Repair or On Board Maintenance.

PRODUCT INFORMATION

Colour	HTA097-Aluminium
Finish/Sheen	Gloss
Converter/Curing Agent	Not applicable
Volume Solids	45% (ISO 3233:1998)
Typical Film Thickness	1.0 mils (25 microns); 2.2 mils (56 microns) wet
Theoretical Coverage	733 ft²/US gal (18 m²/lt) at 1.0 mils (25 microns) dft, allow appropriate loss factors.
Method of Application	Brush, Conventional Spray, Roller
Flash Point	Single Pack 77°F (25°C)

Drying Information

	41°F (5°C)	59°F (15°C)	77°F (25°C)	95°F (35°C)
Touch Dry [ISO 1517:73]	90mins	60mins	30mins	15mins
Hard Dry [ISO 9117:90]	5hrs	3hrs	2hrs	60mins

Overcoating Data - see limitations

	Substrate Temperature							
	41°F (5°C)		59°F (15°C)		77°F (25°C)		95°F (35°C)	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Intertherm 50	24hrs	ext	16hrs	ext	12hrs	ext	6hrs	ext

REGULATORY DATA **VOC** 495 g/lt (4.13 lbs/US gal) calculated

CERTIFICATION

When used as part of an approved scheme, this material has the following certification:

- Fire Resistance - Surface Spread of Flame (WFR) - (IMO Resolution A653 (16))
- Fire Resistance - Marine Equipment Directive compliant

Consult your International Representative for details

**SYSTEMS AND
COMPATIBILITY**

Consult your International Representative for the system best suited for the surfaces to be protected.

**SURFACE
PREPARATIONS**

Use in accordance with the standard Worldwide Marine Specifications.

All surfaces to be coated should be clean, dry and free from contamination.

High pressure fresh water wash or fresh water wash, as appropriate, and remove all oil or grease, soluble contaminants and other foreign matter in accordance with SSPC-SP1 solvent cleaning.

NEWBUILDING

Intertherm 50 is suitable for application to steelwork freshly coated with zinc silicate shop primers. If the zinc shop primer shows extensive or widely scattered breakdown, or excessive zinc corrosion products, overall sweep blasting will be necessary. Ensure that the zinc primer is fully cured prior to the application of Intertherm 50 by following the curing instructions on the relevant product data sheet. Other types of shop primer are not suitable for overcoating and will require complete removal by abrasive blast cleaning. Weld seams and damaged areas should be blast cleaned to Sa2½ (ISO 8501-1:1988).

MAJOR REFURBISHMENT

Abrasive blast clean to Sa2½ (ISO 8501-1:1988).

REPAIR/OBM

Intertherm 50 may be applied directly over aged Intertherm 50 following thorough fresh water washing and degreasing provided the coating to be overcoated is in an intact and tightly adherent condition. Loose or flaking coatings should be removed back to firm edge and Intertherm 50 or an appropriate primer should be used to repair the area before application of the full coat.

Consult your International Representative for specific recommendations.

NOTE:

**For use in Marine situations in North America, the following surface preparation standards can be used:
SSPC-SP10 in place of Sa2½ (ISO 8501-1:1988)**

APPLICATION

Mixing	This material is a one pack coating and should always be mixed thoroughly with a power agitator before application.
Thinner	Not recommended. Use International GTA007 only in exceptional circumstances (max 5% by volume). DO NOT thin more than allowed by local environmental legislation.
Airless Spray	Not recommended.
Conventional Spray	Gun DeVilbiss MBC or JGA Air Cap 704 or 765 Fluid Tip E
Brush	Recommended.
Roller	Recommended
Cleaner	International GTA007
Work Stoppages and Cleanup	Thoroughly flush all equipment with International GTA007. All unused material should be stored in tightly closed containers. Partially filled containers may show surface skinning and/or a viscosity increase of the material after storage. Material should be filtered prior to use.
Welding	In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation. In North America do so in accordance with instruction in ANSI/ASC Z49.1 "Safety In Welding and Cutting".

SAFETY

All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety & Environmental standards and regulations.
Prior to use, obtain, consult and follow the Material Safety Data Sheet for this product concerning health and safety information. Read and follow all precautionary notices on the Material Safety Data Sheet and container labels. If you do not fully understand these warnings and instructions or if you can not strictly comply with them, do not use this product. Proper ventilation and protective measures must be provided during application and drying to keep solvent vapour concentrations within safe limits and to protect against toxic or oxygen deficient hazards. Take precautions to avoid skin and eye contact (ie. gloves, goggles, face masks, barrier creams etc.) Actual safety measures are dependent on application methods and work environment.

EMERGENCY CONTACT NUMBERS:

USA/Canada - Medical Advisory Number 1-800-854-6813

Europe - Contact (44) 191 4696111. For advice to Doctors & Hospitals only contact (44) 207 6359191

R.O.W. - Contact Regional Office (see page 4 of Data Sheet)

LIMITATIONS

Intertherm 50 is not suitable for exposure in acid or alkaline conditions.

Do not over apply. Application above 40 microns (1.6 mils) dft will result in blistering when subject to high temperatures.

Overcoating information is given for guidance only and is subject to regional variation depending upon local climate and environmental conditions. Consult your local International Representative for specific recommendations.

Apply in good weather. Temperature of the surface to be coated must be at least 3°C (5°F) above the dew point. For optimum application properties bring the material to 21-27°C (70-80°F), unless specifically instructed otherwise, prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage in accordance with information given in the STORAGE Section of this data sheet. Technical and application data herein is for the purpose of establishing a general guideline of the coating application procedures. Test performance results were obtained in a controlled laboratory environment and International makes no claim that the exhibited published test results, or any other tests, accurately represent results actually found in all field environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection, verification of performance and use of the coating.

In the overcoating data section 'ext' = extended overcoating period. Please refer to the International Marine Painting Guide - Definitions and Abbreviations available on our website.

UNIT SIZE

5 litres in a 5 litre container.

5 US gallons in a 5 US gallon container

For availability of other unit sizes consult International

UNIT SHIPPING WEIGHT

5 litre unit: 6.2 kg

5 US gallon unit - 50.5 lbs (22.9 kg)

STORAGE

Shelf Life

12 months minimum at 77°F (25°C). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.

WORLDWIDE AVAILABILITY

Consult International.

DISCLAIMER

The information in this data sheet is not intended to be exhaustive: any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. All advice we give or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to law) any loss or damage arising out of the use of the product. All products supplied and technical advice given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check that this data sheet is current prior to using the product. It is the user's responsibility to check with his local International representative that this data sheet is current prior to using the product.

International and product names mentioned in this data sheet are trademarks of, or licensed to, Akzo Nobel. © Akzo Nobel 2003

Regional Addresses
Head Office

International Coatings Ltd
 Oriol House
 16 Connaught Place
 London W2 2ZB
 United Kingdom
 tel: +44 (0) 207 479 6000
 fax: +44 (0) 207 479 6500

www.international-marine.com

European Region

International Coatings Ltd
 Stonegate Lane
 Felling, Gateshead
 Tyne & Wear NE10 0JY
 United Kingdom
 tel: +44 (0) 191 469 6111
 fax: +44 (0) 191 438 3977

Asia Region

International Coatings Pte Ltd
 3 Neythal Road
 Jurong Town
 Singapore 628570
 tel: +65 261 5033
 fax: +65 264 4612

Australasia Region

Akzo Nobel Pty Ltd
 Batavia House
 6 Grand Avenue
 Camellia, 2142, NSW
 Australia
 tel: +61 2 96384555
 fax: +61 2 98980470

North American Region

International Paint Inc
 6001 Antoine Drive
 Houston
 Texas 77091
 United States of America
 tel: +1 (713) 682 1711
 fax: +1 (713) 684 1511

South American Region

Akzo Nobel Ltda
 Av. Paiva 999 - Neves
 Sao Goncalo/RJ
 24426-140
 Brazil
 tel: +55 (0) 21 2624 7100
 fax: +55 (0) 21 2624 7125